IN THE CLAIMS

1-29. (canceled)

- 29. (Currently amended): A grease for use in a rolling bearing comprising a base grease and an additive, wherein the base grease comprises a base oil and a thickener, said base oil is one oil selected from among poly-α-olefin oil, mineral oil, and ether oil, said base oil having a kinematic viscosity of 33 to 100mm²/s at 40°C and the additive comprises The grease according to claim 1, wherein said imorganic bismuth compounds are sodium bismuthate.
- 30 (previously presented) A grease for use in a rolling bearing comprising a base grease and an additive, wherein the base grease comprises a base oil and a thickener, said base oil is one oil selected from among poly- α -olefin oil, mineral oil, and ether oil, said base oil having a kinematic viscosity of 20 to $200 \, \text{mm}^2/\text{s}$ at 40°C and the additive comprises sodium bismuthate
- 31.(new): The grease as defined in claim 30 where the rolling bearing is in a rolling stock.